

परीक्षण रिपोर्ट
TEST REPORT

को जारी / Issued to

M/s. Pravin Bottelings,

**S.F.No.8/3 Paari Nagar, Balaji Nagar West Main
Road, Mamarathupalayam, Periyasemur Post,
Erode - 638 004.**



क्र.सं / Sl. No. **24523**

रिपोर्ट सं / **REPORT NO. : 63153**

Pages.....Nos. Part A,B,C & D

दिनांक / Date : **09.06.2020**

Ltr dtd. 21.05.2020

संदर्भ / Ref. :

परीक्षण मानक स्तर के अनुसार परीक्षण रिपोर्ट / **TEST REPORT AS PER TEST STANDARD : Refer Part C**

भाग - क / PART - A

प्रस्तुत सैपिल का विवरण / PARTICULARS OF SAMPLE SUBMITTED

अ) सैपिल का नाम / a) Name of the Sample	5 litre pet jar & 1 litre pet bottle -as stated by the party
आ) सैपिल प्राप्त होने की तारीख / b) Date of Receipt of sample	21.05.2020
इ) ग्रेड/प्रकार/आकार/वर्ग / c) Grade / variety / type / size / class	--
ई) घोषित मूल्य / d) Declared value, If any	Not applicable
उ) कोड सं. / e) Code No.	Not applicable
ऊ) बैच सं. एवं निर्माण तारीख / f) Batch No. and Date of Manufacture:	Not applicable
ऋ) मात्रा / g) Quantity	02 Samples
ऐ) पैकिंग की रीति / h) Mode of Packing	Not Packed
ओ) मोहर बंद या नहीं / i) Sealed or not	Not sealed
ओ) कोई अन्य सूचना / j) Any other information	-

भाग - ख / PART - B

अनुपूरक सूचनाएँ / SUPPLEMENTARY INFORMATIONS

अ) सैपिलिंग कार्यवाहियों हेतु संदर्भ / a) Reference to sampling procedure	: Sampling not done by this lab
आ) माप करने हेतु लिए गए सहायक दस्तावेज एवं प्राप्त परिणाम b) Supporting documents for the measurement taken and result derived	: As given in Part C
इ) संबंधित कार्य अनुदेशों में निर्धारित के अनुसार परीक्षण रीति से कोई परिवर्तन c) Deviation from the test method as prescribed in relevant work instructions, if any	: No deviation from the standard

रिपोर्ट सं / REPORT NO. : 63153

दिनांक / Date :

09.06.2020



क्र.सं / Sl. No.

24523

भाग - ग / PART - C

परीक्षण परिणाम / TEST RESULTS

Test Duration: 22.05.2020 to 27.05.2020

Sl. No.	Property	Standard	Unit	Results obtained		
				5 litre pet jar	1 litre pet bottle	
1	Overall migration in n-heptane @ 38 °c for 30 minutes	IS-12252	mg/dm ²	0.14	--	Max 10.0
			mg/l	--	0.16	Max 60.0
2	Colour Migration in extracted 'n' heptane	IS-9845	--	No visible colour migration	No visible colour migration	Colour migrated to extracted simulant shall not be apparent to naked eye.
3	Thickness	--	mm	0.30	0.23	--
4	Material Identification by DSC	--	--	Polyethylene Terephthalate (PET)	Polyethylene Terephthalate (PET)	--

PART - D

REMARKS - Nil

NOTE:

1. The results related only to the items tested as supplied by the party.
2. The test certificate shall not be reproduced in full except without the written approval of the laboratory.
3. The Test Report / Certificate is issued only for the samples submitted to CIPET
4. The Quality of the subsequent production lot has to be ensured by the purchaser

2 of



AUTHORISED SIGNATORY



AUTHORISED SIGNATORY


2020-5-60 (5 lit jar)

DSC25, 5/27/2020 2:24:36 PM
5.00000 mg
Tzero Aluminum

cipet chn

C:\DSC Data\2020-5-60 (5 lit jar).tri

2020-5-60 (5 lit jar)



PET

DSC25, 5/27/2020 3:06:54 PM
5.00000 mg
Tzero Aluminum

2020-5-60 (1Lit bottle)

cipet chn
C:\DSC Data\2020-5-60 (1Lit bottle).tri

2020-5-60 (1Lit bottle)

